



Classique Collection

Technical Specifications

Reference	Composition	Horizontal Repeat/cm	Vertical Repeat/cm	Width/cm	Weight gr/m ²	Pilling [UNI EN ISO 12945-1]	Martindale/rubs [UNI EN ISO 12947-2]	Dimensional Stability	Keeping
12	100% Polyester	–	–	290	242 [-/+ 5%]	4	30.000	- 1% - 1.5%	    
A23	45% Polyester 35% Acetate 20% Viscose	47	70	290 Railroaded	417 [-/+ 5%]	4	35.000	- 1% - 1.5%	    
A24	45% Polyester 35% Acetate 20% Viscose	21	23.5	290 Railroaded	440 [-/+ 5%]	4	35.000	- 1% - 1.5%	    
A33	45% Polyester 35% Acetate 20% Viscose	20	35	290 Railroaded	433 [-/+ 5%]	4	35.000	- 1% - 1.5%	    
A35	70% Polyester 30% Acetate	68	70	290 Railroaded	287 [-/+ 5%]	4	35.000	- 1% - 1.5%	    
A36	45% Polyester 35% Acetate 20% Viscose	33	35	290 Railroaded	399 [-/+ 5%]	4	30.000	- 1% - 1.5%	    
A37	45% Polyester 35% Acetate 20% Viscose	44	70	290 Railroaded	415 [-/+ 5%]	4	30.000	- 1% - 1.5%	    
A38	45% Polyester 35% Acetate 20% Viscose	1.5	1.5	290	391 [-/+ 5%]	4	30.000	- 1% - 1.5%	    
A60	100% Polyester	0.5	–	290	240 [-/+ 5%]	4	35.000	- 1% - 1.5%	    
A142	100% Polyester	65	70	290 Railroaded	241 [-/+ 5%]	4	35.000	- 1% - 1.5%	    
Velvet	60% Viscose 40% Cotton	–	–	140	428 [-/+ 5%]	4	50.000	- 1% - 1.5%	    