



Renoir Collection

FIRE RESISTANT [CLASSE 1]

Technical Specifications

Reference	Composition	Horizontal Repeat/cm	Vertical Repeat/cm	Width/cm	Weight gr/m ²	Pilling [UNI EN ISO 12945-1]	Martindale/rubs [UNI EN ISO 12947-2]	Dimensional Stability	Keeping
7797	100% Polyester FR	72	43	290	478 [-/+ 5%]	4	40.000	- 1% - 1.5%	    
7815	100% Polyester FR	5	17	290	482 [-/+ 5%]	4	40.000	- 1% - 1.5%	    
7831	100% Polyester FR	35	18	290 Railroaded	400 [-/+ 5%]	4	40.000	- 1% - 1.5%	    
7836	100% Polyester FR	18	22	290	380 [-/+ 5%]	4	40.000	- 1% - 1.5%	    
7837	100% Polyester FR	35	24	290 Railroaded	386 [-/+ 5%]	4	40.000	- 1% - 1.5%	    
7839	100% Polyester FR	75	69	290	397 [-/+ 5%]	4	40.000	- 1% - 1.5%	    
7840	100% Polyester FR	–	–	290	351 [-/+ 5%]	4	40.000	- 1% - 1.5%	    
7841	100% Polyester FR	–	–	290	437 [-/+ 5%]	4	40.000	- 1% - 1.5%	    